

	Product Data Sheet	Issue Date : 01.01.10
Product Name	Futura ClearFastPET - Type 103	Old Type No. 940401C

Recommended Applications

- ▶ Aqua and Carbonated Soft Drink (CSD) Bottles.

Product Features

- ▶ Futura ClearFastPET is a PET based copolymer resin containing IPA as a comonomer.
- ▶ Futura ClearFastPET is formulated with special additives that can deliver excellent clarity and rigidity.
- ▶ Futura ClearFastPET exhibits fast reheat characteristics required for high speed stretch blow molding machine. The resin does not leave behind any grayish tinge to the blown containers.
- ▶ Futura ClearFastPET is in full compliance with USFDA regulations, EU and HBB Canada norms.

Properties

Characteristic	Unit	Type 103			Test Method
		A	B	C	
Intrinsic Viscosity @ 30°C	dL/g	0.76 ± 0.02	0.80 ± 0.02	0.84 ± 0.02	FPL-QP-V-20-58
b* Color	CIE Lab	-1 max.	-1 max.	-1 max.	FPL-QP-S-20-55-Part-B-XXI
Carboxyl Number	meq/kg	25 max.	25 max.	25 max.	FPL-QP-T-20-55-Part-B-VIII
Melting Point	°C	246 ± 2	246 ± 2	246 ± 2	FPL-QP-DSC-20-55-Part-B-XVIII #
Acetaldehyde	ppm	1.0 max.	1.0 max.	1.0 max.	FPL-QP-GC-20-55-Part-B-XII
Bulk Density	g/cc	0.85 ± 0.10	0.85 ± 0.10	0.85 ± 0.10	FPL-QP-P-20-55-Part-B-XX
Weight of 20 Chips	mg	300 ± 50	300 ± 50	300 ± 50	FPL-QP-W-20-55-Part-A-I
Moisture (when packed)	wt. %	0.25 max.	0.25 max.	0.25 max.	FPL-QP-E-20-55-Part-B-VI

Determined using DSC second heating cycle.

Processing Parameters

a) Drying Condition

Granules must be thoroughly dried before processing to limit the occurrence of hydrolytic degradation.

Drying temperature	165 ± 5 °C
Drying time	4- 5 hours
Dew point	- 40 °C
Residual moisture content	≤ 25 ppm

b) Process Temperature** (Injection Stretch Blow Molding)

Barrel Temperature	285 ± 5 °C
Mold Temperature	285 ± 5 °C
Preform Temperature	110 ± 5 °C

** The values quoted above are typical numbers for benchmarking. Individual machine parameters should be determined on a case-by-case depending on the design of the product(s).

Packing

Resin can be supplied in 1000 kg PP jumbo bags with LDPE liner at 20 bags per 20 ft FCL container as required.

Contact Address

Futura Polymers, a division of Futura Polyesters Limited, 1-A Kamarajar Salai, Manali, Chennai, India - 600 068.	Tel : + 91 44 25941313 – 17, 25941704 – 05 Fax : + 91 44 25941615, 1054, 1566 e-mail : futurach@futura polyesters.com Web : www.futura polyesters.com
---	--

All products are under continual improvement. Rights are reserved to modify product/process without prior notice subject to performance criteria as per product data sheet