

	Product Data Sheet	Issue Date : 01.10.11
Product Name	Futura TexPET - Super Bright Type 201	Old Type No. 20100

Recommended Applications

- Textile / Fiber applications.

Product Features

- Futura TexPET-Super Bright is a Polyester based resin without TiO₂.

Properties

Characteristic	Unit	Type 201	Test Method
		SPB-Y3	
Intrinsic Viscosity @ 25°C	dL/g	0.63 ± 0.01	FPL-QP-V-20-58
b* Color	CIE Lab	3 max.	FPL-QP-S-20-55-Part-B-XXI
Carboxyl Number	meq/kg	35 max.	FPL-QP-T-20-55-Part-B-VIII
Melting Point	°C	252 ± 2	FPL-QP-DSC-20-55-Part-B-XVIII #
DEG	wt. %	1.5 max.	FPL-QP-GC-20-55-Part-B-XIII
Weight of 20 Chips	mg	300 ± 50	FPL-QP-W-20-55-Part-A-I
Moisture (when packed)	wt. %	0.25 max.	FPL-QP-E-20-55-Part-B-VI

Determined using DSC second heating cycle.

Packing

Resin can be supplied in 900 kg PP jumbo bags with LDPE liner at 20 bags per 20 ft FCL container as required.

Contact Address

Futura Polymers,
a division of Futura Polyesters Limited,
1-A Kamarajar Salai, Manali,
Chennai, India - 600 068.

Tel : + 91 44 25941313 – 17, 25941704 – 05
Fax : + 91 44 25941615, 1054, 1566
e-mail : futurach@futura-polyesters.com
Web : www.futura-polyesters.com

All products are under continual improvement. Rights are reserved to modify product/process without prior notice subject to performance criteria as per product data sheet